

PRIMER #2

MARSEAL® exterior grade, solvent-based asphalt primer. Used to prime the substrate before application of MARSEAL® surface-adhered linings. Acceptable substrates include concrete, masonry block, brick, metal, and wood.

SPECIFICATIONS

COVERAGE RATE:

150 to 200 square feet per US gallon.

DRYING TIME:

2 hours at 77°F (25°C) and 50% relative humidity. Drying time will vary with changes in temperature or humidity.

SHELF LIFE:

One year at 77°F (25°C) and 50% relative humidity.

| TYPICAL PHYSICAL PROPERTIES | |
|-----------------------------|---|
| Color | Black |
| % Solids | By Weight - 56% By Volume - 52% |
| Volatile Organic Compounds | Compliant. Meets ASTM D41. No asbestos used. |



APPLICATOR NOTES

1. Substrate surface should be clean, smooth, and dry. Vacuum or brush off all dirt, laitance, etc. Metal substrate surfaces should be rust-free. If blasting is required, SSPC #1 or NACE Standard #5 should be followed.
2. Ready to apply. No mixing required.
3. Do not thin. Use as provided.
4. Can be applied by sprayer (either compressed air or airless), roller, or brush.

DISCLAIMER:

The above guidelines are based on general industry practices and not applicable to all installations. Please contact Blair Rubber Company for specific application instructions. Application methods shall conform to Blair Rubber Company instructions contained in the Engineering & Applicator manual. Deviations from the specifications must be approved in writing by Blair Rubber Company. Data values are approximate and may vary based on installation techniques and atmospheric conditions. As such, data values should be used as general guidelines and are not a legally binding warranty of product characteristics. This document is copyright to and the intellectual property of Blair Rubber Company and may not be copied or distributed without prior consent.