

RC621BC

EnduraflexTM black, soft, cured chlorobutyl lining for field lining and repair. Not recommended for NaOCl (bleach) service. FDA compliant.

SPECIFICATIONS

FACE MATERIAL DUROMETER,
55 to 65 A

AVAILABLE GAUGES:

1/8", 3/16", 1/4", 4mm, 5mm, 6mm

SKIVE:

Open or Butt & Cap

REPAIRS:

Repair with original lining
See Section 16 – Repair Procedures.

TYPICAL PHYSICAL PROPERTIES

Tensile Strength PSI	ASTM D412	1000
% Elongation at Break	ASTM D412	550
Durometer	ASTM D2240	60 A
Specific Gravity	ASTM D297	1.39
Adhesion to Metal	ASTM D429	25LBS

CURE METHODS AND TIMES:

Lining is cured. No additional curing required.



