

APPLICATION STEPS FOR SELF-ADHERED MEMBRANE



1. SURFACE PREPARATION

Start all MARSEAL® installations with smooth, clean, dry substrate, free of large voids, loose aggregate, and sharp projections. Blasting is not required if the surface is clean and smooth. Spalled or missing concrete must be repaired at least 1 week prior to membrane installation



2. PRIMING

Priming is required to improve the bond strength of MARSEAL® to the substrate. MARSEAL® Primer should be applied to all surfaces to be lined using a roller or brush.

Allow primer to dry to the touch before lining application. (approximately 1 hour)



3. INSTALLING WALL SHEETS

Measure and pre-cut MARSEAL® lining into appropriate wall and floor length before the installation starts.

Apply lining to the wall area first, allowing 6" to extend over the top of the wall. Lay each adjacent sheet with a 3" side lap (fully cover lay line to ensure proper lap).



4. ROLLING WALL SHEETS

After each sheet is applied, use wall roller to tightly adhere sheet to primed surface.

