

CC4624

Crislip™ black, soft, chlorobutyl for maximum service life in concentrated NaOCl (bleach) service

SPECIFICATIONS

Durometer of Face Material:

Shore A Scale

Atmospheric Cure:

50-65 A

Pressure Cure:

55-65 A

Skive:

Butt & Cap with CC4624

Repairs:

Repair with original lining

See Section 16 – Repair Procedures

Storage Life from Date of Shipment:

32°F (0°C) to 50°F (10°C) – 180 days

51°F (13°C) to 65°F (19°C) – 90 days

66°F (21°C) to 75°F (23°C) – 60 days

76°F (23°C) to 85°F (30°C) – 30 days

* Storage temperature must not exceed 85°F (30°C).

CURE METHODS AND TIMES:

| | |
|-------------------|--|
| Autoclave | 4 hour at 287°F (141°C) |
| Internal Pressure | 10 hours at 240°F (112°C) or 5 hours at 260°F (126°C) |
| Atmospheric | 40 hours at 200°F (94°C) |

Note: Cure times may require adjustment to compensate for heavy metal thickness, low exterior temperatures or other unusual factors. See Section 14 – Curing Instructions.

ADHESIVE SYSTEM

| | |
|-------------------------------|--------------|
| 1 st Coat on Metal | Chemlok® 289 |
| 2 nd Coat on Metal | Chemlok® 290 |
| 3 rd Coat on Metal | Chemlok® 286 |
| On the rubber | Chemlok® 286 |
| Cap And Seams | Tack 500 |

* Each adhesive component requires thorough mixing before application.

TYPICAL PHYSICAL PROPERTIES

| | | |
|-----------------------|------------|---------|
| Tensile Strength PSI | ASTM D412 | 1200 |
| % Elongation at Break | ASTM D412 | 265 |
| Durometer | ASTM D2240 | 60 A |
| Specific Gravity | ASTM D927 | 1.39 |
| Adhesion To Metal | ASTM D429 | 30 lbs. |

APPLICATOR NOTES

1. Plying up layers of rubber lining thicker than 1/4" could result in the rubber flowing or sagging during cure. Test plate is required to determine flow characteristics.
2. The temperature of the substrate must be greater than 60°F (15°C) prior to applying primer and rubber. Temperatures should not exceed 120°F (49°C).
3. A heated table that warms rubber to approximately 120°F (49°C) prior to application is recommended.
4. Strict adherence to adhesive specifications is required. Tack time is critical to the success of the bond.
5. When CC4624 is utilized in HCl service, lap seams may be substituted for cap strips and Chemlok 286 Tack cement may be employed. This method is not recommended for bleach service.

Disclaimer: The above guidelines are based on general industry practices and not applicable to all installations. Please contact Blair Rubber company for specific application instructions. Application methods shall conform to Blair Rubber Company instructions contained in the Engineering & Applicator manual. Deviations from the specifications must be approved in writing by Blair Rubber Company. Data values are approximate and may vary based on installation techniques and atmospheric conditions. As such, data values should be used as general guidelines and are not a legally binding warranty of product characteristics. This document is copyright to and intellectual property of Blair Rubber company and may not be copied or distributed without prior consent.