

MR80

Marflex™ black, ebonite natural rubber lining with excellent machinability.

SPECIFICATIONS

Durometer of Face Material:

Shore A Scale

Pressure Cure:

75-85 D

Skive:

Closed

Repairs:

Repair with original lining

See Section 16 – Repair Procedures

Storage Life from Date of Shipment:

32°F (0°C) to 50°F (10°C) – 180 days

51°F (13°C) to 65°F (19°C) – 90 days

66°F (21°C) to 75°F (23°C) – 60 days

76°F (23°C) to 85°F (30°C) – 30 days

* Storage temperature must not exceed 85°F (30°C).

Caution: Natural rubber is susceptible to deterioration by sunlight and oxygen. This is known as ‘weather checking. Do not expose rubber lining to sunlight, ozone or oxygen.

CURE METHODS AND TIMES:

Autoclave	4 hours at 298°F (148°C)
-----------	--------------------------

Note: Cure times may require adjustment to compensate for heavy metal thickness, low exterior temperatures or other unusual factors. See Section 14 – Curing Instructions.

ADHESIVE SYSTEM

1 st Coat on Metal	Chemlok® 289
-------------------------------	--------------

2 nd Coat on Metal	Chemlok® 290
-------------------------------	--------------

3 rd Coat on Metal	Chemlok® 286
-------------------------------	--------------

On the rubber	Chemlok® 286
---------------	--------------

* Each adhesive component requires thorough mixing before application.

TYPICAL PHYSICAL PROPERTIES

Tensile Strength PSI	ASTM D412	4200
----------------------	-----------	------

% Elongation at Break	ASTM D412	<5
-----------------------	-----------	----

Durometer	ASTM D2240	82 D
-----------	------------	------

Specific Gravity	ASTM D927	1.13
------------------	-----------	------

Adhesion To Metal	ASTM D429	30 lbs.
-------------------	-----------	---------

APPLICATOR NOTES

1. Plying up layers of rubber lining thicker than 1/2” could result in an exothermic reaction or blistering during cure. Test plate is required to determine cure characteristics.
2. The temperature of the substrate must be greater than 60°F (15°C) prior to applying primer and rubber. Temperatures should not exceed 120°F (49°C).
3. A heated table that warms rubber to approximately 120°F (49°C) prior to application is recommended.
4. Strict adherence to adhesive specifications is required. Tack time is critical to the success of the bond.
5. Caution: Hard rubber linings may crack when subjected to thermal or mechanical shock.

Disclaimer: The above guidelines are based on general industry practices and not applicable to all installations. Please contact Blair Rubber company for specific application instructions. Application methods shall conform to Blair Rubber Company instructions contained in the Engineering & Applicator manual. Deviations from the specifications must be approved in writing by Blair Rubber Company. Data values are approximate and may vary based on installation techniques and atmospheric conditions. As such, data values should be used as general guidelines and are not a legally binding warranty of product characteristics. This document is copyright to and intellectual property of Blair Rubber company and may not be copied or distributed without prior consent.