

## VE824WN

Enduraflex™ white, semi-hard natural rubber lining for general purpose and water demineralization. FDA compliant.

### SPECIFICATIONS

#### Durometer of Face Material:

Shore A Scale

#### Atmospheric Cure:

80-90 A

#### Pressure Cure:

75-85 A

#### Skive:

Closed

#### Repairs:

Repair with original lining or C825WN  
See Section 16 – Repair Procedures

#### Storage Life from Date of Shipment:

32°F (0°C) to 50°F (10°C) – 180 days  
51°F (13°C) to 65°F (19°C) – 90 days  
66°F (21°C) to 75°F (23°C) – 60 days  
76°F (23°C) to 85°F (30°C) – 30 days

\* Storage temperature must not exceed 85°F (30°C).

Caution: Natural rubber is susceptible to deterioration by sunlight and oxygen. This is known as 'weather checking'. Do not expose rubber lining to sunlight, ozone or oxygen.

### APPLICATOR NOTES

1. Plying up layers of rubber lining thicker than 1/4" could result in the rubber flowing or sagging during cure. Test plate is required to determine flow characteristics.
2. The temperature of the substrate must be greater than 60°F (15°C) prior to applying primer and rubber. Temperatures should not exceed 120°F (49°C).
3. A heated table that warms rubber to approximately 120°F (49°C) prior to application is recommended.
4. Strict adherence to adhesive specifications is required. Tack time is critical to the success of the bond.
5. Caution: Hard rubber linings may crack when subjected to thermal or mechanical shock.

#### CURE METHODS AND TIMES:

Autoclave	2 hours at 260°F (127°C)
Internal Pressure	8 hours at 260°F (127°C)
Atmospheric	Step 1 – Observe a gradual warm-up time until reaching 160°F (71°C).
	Step 2 - 24 hours at 180°F (82°C) or 20 hours at 200°F (94°C)

Note: Cure times may require adjustment to compensate for heavy metal thickness, low exterior temperatures or other unusual factors. See Section 14 – Curing Instructions.

#### ADHESIVE SYSTEM

1 <sup>st</sup> Coat on Metal	Chemlok® 289
2 <sup>nd</sup> Coat on Metal	Chemlok® 290
3 <sup>rd</sup> Coat on Metal	Chemlok® 286 or Tack 103
On the rubber	Chemlok® 286 or Tack 103

\* Each adhesive component requires thorough mixing before application.

#### TYPICAL PHYSICAL PROPERTIES

Tensile Strength PSI	ASTM D412	1500
% Elongation at Break	ASTM D412	150
Durometer	ASTM D2240	80 A
Specific Gravity	ASTM D927	1.48
Adhesion To Metal	ASTM D429	30 lbs.

Disclaimer: The above guidelines are based on general industry practices and not applicable to all installations. Please contact Blair Rubber company for specific application instructions. Application methods shall conform to Blair Rubber Company instructions contained in the Engineering & Applicator manual. Deviations from the specifications must be approved in writing by Blair Rubber Company. Data values are approximate and may vary based on installation techniques and atmospheric conditions. As such, data values should be used as general guidelines and are not a legally binding warranty of product characteristics. This document is copyright to and intellectual property of Blair Rubber company and may not be copied or distributed without prior consent.